

100% SYNTHETIC TIRE & PAD LUBRICANT WITH GRAPHITE FOR ROTARY KILNS

XL-0854 is a custom blend of **synthetic polymers** and performance enhancing additives expressly designed to slowly evaporate at high temperatures leaving **absolutely no abrasive residues**.

XL-0854's specially formulated additives including **high concentrations of solid boundary lubricants** are designed to lubricate tires and pads under the most severe and critical operating conditions.

XL-0854 Will reduce friction, thereby reducing:

- Tire & pad wear
- Kiln "creepage"
- Flexing of the kiln shell
- Shell ovality
- Replacement of tire shell sections

XL-0854 has been used successfully at operating temperatures from -40°C to 600°C.

TYPICAL SPECIFICATIONS					
Product Code: XL-0854	/000	/001	/002	/003	/004
N.L.G.I. Grade:	0	1	2	3	4
Penetration @ 25°C (ASTM D-217)	360	365	265	240	180
After 60 strokes	365	331	268	240	185
After 10,000 strokes	367	335	273	247	185
After 60,000 strokes	372	343	275	255	200
Dropping Point (°C) (ASTM D-2265)	None				
Melting Point (°C)	None				
Copper Strip Test (163°C for 3 hours) (ASTM D-130)	Negative				
Texture	Adhesive/Tacky				
Colour	Black				
Timken OK Load (kg/lbs) (ASTM D-2509)	40/90	40/90	40/90	40/90	40/90
Type of thickener	Inorganic				
Oil Separation (24hrs @ 25°C) (ASTM D-1742)	< 1%	< 1%	< 1%	< 1%	< 1%
Additives	Graphite, Anti-rust, Anti-corrosion				
Temperature Range (°C)	-40 to 600				
Maximum Intermittent Temperature (°C)	650				
Minimum Temperature (°C)	-40	-40	-30	-15	0
Base Oil Viscosity (cSt @ 100°C) (ASTM D-445)	200				



255 avenue Labrosse, Pointe-Claire, Quebec, Canada H9R 1A3
Tel: 514-694-5823 | 800-567-5823 | Fax: 514-694-8628 | www.thermal-lube.com

The information presented in this bulletin is, to the best of our knowledge, accurate. It is intended to be helpful, and is not to be considered a guarantee.

