

## MEDIUM DRYING FILM LUBRICANT WITH MOLYBDENUM

**XL-2353** offers excellent extreme pressure dry film lubrication. This specially processed synthetic / solvent- based long-wearing molybdenum disulfide coating material dries slowly at elevated temperatures.

### ADVANTAGES

- Low coefficient of friction
- Excellent release properties.
- Minimum surface pre-treatment.
- Easy application.

**XL-2353** can be applied to all substances not affected by the Mineral Spirits fluid component, or the Polyolester carrier oil.

PHYSICAL PROPERTIES	
<b>XL-2353 (as supplied)</b>	
<b>Lubricant:</b>	Polyolester, Molybdenum Disulfide
<b>Fluid Component:</b>	Mineral Spirits
<b>Colour:</b>	Dark grey
<b>Shelf Life:</b>	One year
<b>XL-2353 (when cured)</b>	
<b>Coefficient of Friction:</b>	0.23 (static)
<b>Service Temperature (°C):</b>	315
<b>Intermittent Temperature (°C):</b>	660



255 avenue Labrosse, Pointe-Claire, Quebec, Canada H9R 1A3  
Tel: 514-694-5823 | 800-567-5823 | Fax: 514-694-8628 | [www.thermal-lube.com](http://www.thermal-lube.com)

The information presented in this bulletin is, to the best of our knowledge, accurate. It is intended to be helpful, and is not to be considered a guarantee.

